

PHOTOSENSITIVE COMPOSITION AND PHOTOSENSITIVE PLANOGRAPHIC PRINTING PLATE

Publication number: JP10097067 (A)

Publication date: 1998-04-14

Inventor(s): HATTORI RYOJI; KUROKI TAKAAKI; MAHASHI TATSUICHI; KAWAKAMI SOTA

Applicant(s): KONISHIROKU PHOTO IND

Classification:

- **International:** G03F7/027; C08F2/50; C08F299/02; G03F7/027; C08F2/46; C08F299/00; (IPC1-7): G03F7/027; C08F2/50; C08F299/02; G03F7/027

- **European:**

Application number: JP19960249912 19960920

Priority number(s): JP19960249912 19960920

Abstract of JP 10097067 (A)

PROBLEM TO BE SOLVED: To obtain a photosensitive planographic printing plate having improve ink receptivity and chemical resistance without deteriorating sensitivity and developability and to obtain a photosensitive compsn. fit for the photosensitive layer of the printing plate. **SOLUTION:** The objective photosensitive compsn. contains a monomer represented by the formula $\text{CH}_2=\text{C}(\text{R}_1)-\text{COO}[(\text{CH}_2)_n-\text{O}]_m$ R, an oligomer or prepolymer having constituent units formed from the monomer or further contains a high molecular polymer having an unsatd. or satd. group and a phenyl group in a side chain and having a wt. average mol.wt. of $\geq 10,000$ and ≥ 80 deg.C glass transition temp. In the formula, R is a substituent such as an unsatd. group, unsubstd. alkyl, hydroxyalkyl or carboxyalkyl, (m) is an integer of ≥ 2 , (n) is an integer of ≥ 3 and R1 is H or methyl.; The objective photosensitive planographic printing plate has a photosensitive layer made of the photosensitive compsn.

Data supplied from the esp@cenet database — Worldwide